

Technical Data

THERMOTECT WR



Kansai Paint Protective Coatings

GENERIC TYPE	Heat Resistant Paint
DESCRIPTION	A heat resistant paint based on inorganic copolymer for preventing CUI (Corrosion Under Insulation)
RECOMMENDED USE	An Insulated and non insulated steel structure for high temperature services
FEATURES	<ul style="list-style-type: none"> - Excellent heat resistance up to 650°C - Cyclic services in temperatures between -185°C ~ 540°C - Suitable for insulated surface - Pre-heating is not required. - Good weather resistance - Good applicability
PHYSICAL PROPERTIES	
Colour	Grey
Finish	Matt
Volume Solids	54 %
Typical Thickness	Dry : 125 microns / coat
Theoretical Coverage	4.4 m ² /L at 125 microns DFT
	*Practical coverage vary depending on loss factors.
Flash Point	Base : 28.5 °C, Hardener : 26.9 °C
Specific Gravity	1.65 g/cm ³
VOC	396 g/L
Temperature Resistance	Non-continuous : 650°C, Continuous : 540°C
*These numerical values are subject to normal manufacturing tolerances, colours and testing variances	

These numerical values are subject to normal manufacturing tolerances, colours and testing variances.

SURFACE PREPARATION

- All surfaces to be coated should be completely clean, dry and free from contamination.
- Surface preparation method shall be in accordance with ISO 8504: 2000.
- Remove salt and other water-soluble contaminants by fresh water.
- Remove oil and grease with suitable detergent or solvent (SSPC-SP-1).
- Remove rust, mill scale and other loose material completely by abrasive blasting (ISO 8501-1:2007 Sa 2 1/2).

APPLICATION	
Application Conditions	Ambient temperature shall be above 5°C and relative humidity shall be below 85%. Surface temperature shall be a minimum of 3°C above dew point. Adequate ventilation shall be provided in confined spaces to ensure proper drying.
Mixing	Stir each component with power agitator well before mixing. Then power mix two components.
Mixing ratio	Base/Hardener = 95/5 by weight
Induction Time	Not required
Application Method	Airless spray Thinner : Enamel Thinner 200 (0~5% by weight) Nozzle pressure: Not less than 10MPa Nozzle Tip : No.163~415~621
Brush/Roller	Thinner : Enamel Thinner 200 (0~5% by weight)

*Too much thinning results sagging and slower cure.

Clean Up	Clean all the equipment with thinner immediately after use.		
Pot Life	10 °C	20 °C	30 °C
	14 hour(s)	12 hour(s)	8 hour(s)
*Use all mixed paint within pot life.			
Drying Time	10 °C	20 °C	30 °C
Surface dry	3 hour(s)	3 hour(s)	2 hour(s)
Touch dry	16 hour(s)	6 hour(s)	6 hour(s)
*Drying time may vary depending on film thickness, ventilation, humidity, undercoat paint condition etc.			
Overcoating Interval	10 °C	20 °C	30 °C
Minimum	24 hour(s)	6 hour(s)	6 hour(s)
Maximum	7 day(s)	7 day(s)	7 day(s)
*The overcoating intervals are based on overcoating with same or same type of paint.			
Typical undercoat	–		
Typical topcoat	THERMOTECT WR		

SAFETY PRECAUTIONS

Detail information is given on Safety Data Sheet (SDS). Avoid inhalation of spray mist or vapour. Avoid skin and eye contact. Paint contacted with skin should be immediately removed with water and/or suitable cleanser. Eyes should be flushed with water and seek immediate medical attention. Since this product contains flammable solvents, keep away from sparks and open flames. Application and handling of this product should be in compliance with relevant national regulations.

STORAGE

Store in dry, cool condition and away from sources of heat and ignition. Containers must be kept tightly closed. Store conditions shall be in accordance with national regulations.

SHELF LIFE

Base: 12 months from date of production, Hardener: 6 months from date of production

GENERAL REMARKS

- It is not suitable for strong steam, acid and alkali environment due to poor resistance.
- Color may turn to reddish at the range more than 300°C. Film performance is not be affected
- The yellowing of the hardener may become stronger during storage, curability or coating quality are not be affected.
- Shake the can of hardener well before use.

*If any inquiries, please consult Kansai Paint representative for further information.

DISCLAIMER : The information given on this sheet is to the best of our knowledge and assurance at the time of issuing. Since conditions of use are beyond the manufacturer's control, information contained herein is without warranty, implied or otherwise, and the suitability of the material for the use contemplated is the sole responsibility of the buyer. The information contained on this data sheet is subject to modification at any time due to our policy of modification and product development.